

In the Specification:

[000037] Pigment mixture:

50.0%-wt. of Naturell BB PlvTM Pigment

50.0%-wt. of Naturell PulverTM Pigment

(from Cosnaderm Chemische Rohstoffe GmbH, D-68526 Ladenburg)

[000038] Used as control examples were:

(6) PET film, aluminised und nicotine-resistant (nontranslucent)

(7) PET film, 15 µm, transparent

(8) ~~Scotchpak~~ SCOTCHPAK[®] (a plastic film) 1006

[000040] Skin patches were produced using the backing layers prepared under 1. To this end, DUROTAK[®] 2052 (National Starch & Chemical B.V.) (a pressure sensitive adhesive) was spread at a weight per unit area of 80 g/m² and in each case covered with one of the backing layers mentioned under 1. Subsequently, individual patches, each patch of a size of 1 cm², were punched out.